



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES (MES)
TEST RESULT FOR FINENESS MODULUS(F.M.) OF SAND.

Page No: 01

Copy no : 01

Job No : 01/2025-2026 (Sand).
Name of Clint : GE (Air) Tejgaon, Dhaka.
Ref ltr no : CE (Air)/164 of 2024-2025/03/E-6 Dt.30 Jun'2025
Project Name : Construction of Water Reservoir.
Sample Specimen : Sylhet Sand.
Dt of sample collection : 01 July'2025
Test Standard : ASTM/BS

Sieve Size	Wt of Material Retained(gms)	Percentage Material Retained(Round)	Cumulative % Retained	%Finer	Remarks
# 4	1.7	0.43	0.43		
# 8	25.61	6.40	6.83		
#16	64.82	16.21	23.03		
# 30	164.2	41.05	64.08		
# 50	121.32	30.33	94.41		FM= 2.88
#100	19.29	4.82	99.24		
# 200	2.38	0.60	..		
#Pan	0.53	0.13	...		
			Σ= 288.02		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to be avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Permissible Value:

- 1.For Sylhet/Domar sand minimum FM will be = 2.50
- 2.For Local sand minimum FM will be = 1.5
- 3.For Vitty sand minimum FM will be = 0.80