



MILITARY ENGINEER SERVICES (MES)

MATERIAL TESTING LABORATORY

Mobile: 01769-012888, <http://mes.org.bd>

M E S
Material Testing
Laboratory

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No	: 04/2026-2027 (Con).	Type of Aggregate	: Brick
Send by	: GE (Army) Jalalabad	Brand & Type of Cement	: Shah Opc.
Ref. No	: CEA/280 of 2025-2026/07/E-6 Dt.02 Jul'26.	Proportion of Mixture	: 1:2:4
Project	: Renewal/Modification/Alternation Bldg No-164	Desired Design Strength	: 1625 Psi
Sample	: Concrete Cylinder	Date of Sample Collection	: 05/07/2026
Location	: East side of 2nd floor.	Date of Test	: 06/07/2026
Test	: Compressive Strength Test of Concrete Cylinder [ASTM C39]		

TEST REPORT

SL No.	Date of casting as per the letter	Specimen Designation/ Frog Mark	Specimen Area	Maximum Load	Crushing Strength	Average Crushing Strength	Mode of Failure
			(Sq. in)	(Lb)	(Psi)	(Psi)	
1	29 Jun'2026 (07 days)	GE (Army)	12.17	39399.62	3237	3309 (22.82 Mpa) (232.65 kg/cm ²)	Combined *
2		GE (Army)	12.17	59124.54	4858		Combined *
3		GE (Army)	12.17	41151.43	3381		Combined *

Note: Samples were received in sealed condition.

*Combined = Mortar and Aggregate Failure.

Observation on Specimen(if any):

1



Report Prepared by :

Test Performed by :

Countersigned by :

MD IKBAL HOSSEN

SAE B/R
AHQ E in C's Br
Wks Dte, Dhaka Cantt.

AHASAN HABIB

AE B/R
Actg SO-III (Lab)
AHQ E in C's Br
Wks Dte, Dhaka Cantt.

MD ATIKUR RAHMAN
MAJOR
OIC (Lab)
AHQ E in C's Br
Wks Dte, Dhaka Cantt.

[1 Mpa=145 psi, 1kg/cm²=14.223 Psi]

Important Note:

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to be avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

