



MATERIALS TESTING LABORATORY MILITARY ENGINEER SERVICES(MES)

Page no: 551

TEST RESULT FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S BARS

Job No : 100/2025-2026 (Steel).	Copy No : 01
Name of Client : AGE (Air) PKP.	Sample Specimen : Length 600mm , Dia 20mm
Ref.ltr.No : EinC/444 2022-2023/49/E-6 Dt.12 Jan'2026	Sample Grade : 72.5
Project Name : Construction of boundary wall with barbed wire fencing.	Frog Mark : BSRM B-500 DWR.
Dt. of Sample Collection: 13 Jan'2026	

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof load	Yield or Proof Strength	Average Yield or Proof load	Ultimate load	Ultimate Strength	Average Ultimate Strength	Ratio	Elongation% (gauge length)		Average Elongation% (gauge length)	
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	(Fult/Fy)	8inch	5d	8inch	5d
1	0.787	0.783	0.4869	1.639	1.639	43070.98	88451	88394	54410.77	111738	111665	1.26	23			
	20.00	19.89	314.1593	2.439		191.59	610		242.03	771						
2	0.787	0.783	0.4869	1.639	2.439	43352.44	89029	610	54517.77	111958	770	1.26	20.5		22	
	20.00	19.89	314.1593	2.439		192.84	614		242.51	772						
3	0.787	0.783	0.4869	1.639	2.439	42705.78	87701	605	54196.76	111299	768	1.27	22			
	20.00	19.89	314.1593	2.439		189.96	605		241.08	768						

Cautions:

1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecture of the samples to be tested.
2. It is recommended that samples are Sent in asecuried and sealed cover/packet/container under signature of the competent authority.
3. In order to avoid fraudulent of the test results,it is recommended that all test reports should be collected by duly authorised person and not by contractor/supplier.

Oservation on Specimen(if any):

1. Diameter & Unit weight of 20 mm bar is less than the standard value but within tolerance limit according to MES Schedule of Rates-2016.

Minimum Standard Requirements (BDS/ISO 6935-2:1991(E))				Minimum Standard Requirements(ASTM A615/A616M-96a)									
Grade	Y/strength N/mm2 or Mpa	Ult.Str N/mm2 or Mpa	Elongation %	ASTM A 615 M		ASTM A 615 M		ASTM A 615/A 615 M					
				Grade	Y/strength psi (kg/cm2)	Ult.Str psi (kg/cm2)	Grade	Y/strength Mpa (kg/cm2)	Ult.Str Mpa (kg/cm2)	Minimum Elongation in 8"(203.2 mm) GL (%)			
									10 mm	13,16,19 mm		22,25 mm	29,32,36 mm
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)	..	7	7	6

Laboratory Technician

Test Performed By

Vetted By