



MATERIALS TESTING LABORATORY MILITARY ENGINEER SERVICES(MES)

Page no: 327

TEST RESULT FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S BARS

Job No : 104/2024-2025 (Steel).

Copy No : 01

Name of Client : GE (Navy) South Chattogram.

Sample Specimen : Length 600mm , Dia 10mm

Ref.ltr.No : CEN/49 of 2024-2025/06/E-6 Dt.22 May'2025.

Sample Grade : 72.5

Project Name : Construction of Road.

Frog Mark : AKS B-500 DWR.

Dt. of Sample Collection : 28 May'2025

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof load	Yield or Proof Strength	Average Yield or Proof load	Ultimate load	Ultimate Strength	Average Ultimate Strength	Ratio	Elongation% (gauge length)		Average Elongation% (gauge length)	
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	(Fult/Fy)	8inch	5d	8inch	5d
1	0.394 10.00	0.395 10.03	0.1217 78.5398	0.417 0.620	0.417 0.620	15748.07 70.05	129361 892	130913 903	18477.75 82.19	151784 1047	152481 1052	1.17	19.5		19	
2	0.394 10.00	0.395 10.03	0.1217 78.5398	0.417 0.620		16034.91 71.33	131718 908		18584.17 82.67	152658 1053		1.16	18.5			
3	0.394 10.00	0.395 10.03	0.1217 78.5398	0.417 0.620		16027.98 71.30	131661 908		18625.81 82.85	153000 1055		1.16	17.5			

Cautions:

1. Samples as supplied to the laboratory have been tested.The laboratory authority does not bear any responsibility as to the representative charecture of the samples to be tested.
2. It is recommended that samples are Sent in asecuried and sealed cover/packet/container under signature of the competent authority.
3. In order to avoid fraudulent of the test results,it is recommended that all test reports should be collected by duly authorised person and not by contractor/supplier.

Ovservation on Specimen(if any):

Minimum Standard Requirements (BDS/ISO 6935-2:1991(E))				Minimum Standard Requirments(ASTM A615/A616M-96a)									
Grade	Y/strength	Ult.Str	Elongation	ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M			
	N/mm2 or Mpa	N/mm2 or Mpa	%	Grade	Y/strength psi (kg/cm2)	Ult.Str psi (kg/cm2)	Grade	Y/strength psi (kg/cm2)	Ult.Str psi (kg/cm2)	Minimum Elongation in 8"(203.2 mm) GL (%)			
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	10 mm	13,16,19 mm	22,25 mm	29,32,36 mm
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)	..	7	7	6

Laboratory Technician

Test Performed By

Vetted By