



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES (MES)
TEST RESULT FOR FINENESS MODULUS(F.M.) OF SAND.

Page No: 183

Copy no : 01

Job No : 104/2024-2025 (Sand).
Name of Clint : GE (Army) PMB.
Ref ltr no : EinC/101 of 2023-2024/20/E-6 Dt.24 Jan'2025
Project Name : Construction of 1 x Gymnasium.
Sample Specimen : Sylhet Sand.
Dt of sample collection : 30 Jan'2025
Test Standard : ASTM/BS

Sieve Size	Wt of Material Retained(gms)	Percentage Material Retained(Round)	Cumulative % Retained	%Finer	Remarks
# 4	1.43	0.36	0.36		
# 8	15.48	3.87	4.23		
#16	68.95	17.24	21.47		
# 30	215.01	53.75	75.22		
# 50	90.5	22.63	97.84		FM= 2.99
#100	7.86	1.97	99.81		
# 200	0.35	0.09	..		
#Pan	0.15	0.04	...		
			Σ= 298.92		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to be avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Permissible Value:

- 1.For Sylhet/Domar sand minimum FM will be = 2.50
- 2.For Local sand minimum FM will be = 1.5
- 3.For Vitty sand minimum FM will be = 0.80



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES (MES)
TEST RESULT FOR FINENESS MODULUS(F.M.) OF SAND.

Page No: 183

Copy no : 02

Job No : 103/2024-2025(Sand).
Name of Clint : GE (Army) PMB.
Ref ltr no : EinC/101 of 2023-2024/20/E-6 Dt.24 Jan'2025
Project Name : Construction of 1 x Gymnasium.
Sample Specimen : Local Sand
Dt of sample collection : 30 Jan'2025
Test Standard : ASTM/BS

Sieve Size	Wt of Material Retained(gms)	Percentage Matarial Retained(Round)	Cumulative % Retained	%Finer	Remarks
# 4	0	0.00	0.00		
# 8	2.01	0.50	0.50		
#16	3.84	0.96	1.46		
# 30	8.96	2.24	3.70		
# 50	190.97	47.74	51.45		FM= 1.52
#100	174.31	43.58	95.02		
# 200	25.4	6.35	..		
#Pan	0.95	0.24	...		
			Σ= 152.14		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In oder to be avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Permissable Value:

- 1.For Sylhet/Domar sand minimum FM will be = 2.50
- 2.For Local sand minimum FM will be = 1.5
- 3.For Vitty sand minimum FM will be = 0.80