



**MATERIAL TESTING LABORATORY**  
**MILITARY ENGINEER SERVICES(MES)**

Page No : 151

Copy no : 01

**TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE**

Job No : 107/2025-2026 (Con).  
Name of Client : GE (Navy) Dhaka.  
Ref ltr no : 6000/Naval HQ CW&MC/84/E-6 Dt.28 Aug'2025.  
Name of the project : Construction of CW&MC and Multipurpose Complex.  
Status of sample : 1st floor roof slab.  
Dt of sample collection: 27 Aug'2025  
Test Standard : ASTM/BS

Sample Specimen: Ht 200mm(8") Dia 100 mm(4")  
Type of Aggregate : Stone  
Brand &Type of Cement : Shah Opc.  
Proportion of Mixture : 1:1.5:3  
Desired Design Strength : 2100 Psi

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	24 Aug'2025 (07 days)	31 Aug'2025	12.17	29221.39	2401	Average of Sample 1, 2 & 3  2374	Combined Failure
2			12.17	29489.41	2423		
3			12.17	27970.64	2298		

**Cautions :**

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result, it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

**Observation on Specimen(if any):**

1

Laboratory Technician

Test Performed By

Vetted By