



**MATERIAL TESTING LABORATORY  
MILITARY ENGINEER SERVICES(MES)**

Page No: 387

Copy no : 01

**TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE**

Job No : 115(D)/2025-2026 (Con).

Name of Client : GE (Navy) Khulna.

Sample Specimen : Ht 200mm(8") Dia 100 mm(4")

Ref Itr no : 6000/Test/39/E-6 Dt.06 Nov'2025.

Type of Aggregate : Stone

Name of the project : Construction of MT pool.

Brand &Type of Cement : Crown Opc.

Status of sample : Ground floor column.

Proportion of Mixture : 1:1.5:3

Dt of sample collection: 09 Nov'2025

Desired Design Strength : 4500 Psi

Test Standard : ASTM/BS

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	03 Nov'2025 (28 days)	01 Dec'2025	12.17	59837.81	4917	Average of Sample 1, 2 & 3  5033	Combined Failure
2			12.17	61068.05	5018		
3			12.17	62845.06	5164		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm<sup>2</sup>=14.223 Psi]