



**MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)**

Page No : 415

Copy no : 02

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 127(D)/2025-2026 (Con).
Name of Client : AGE (Army) Momenshahi. Sample Specimen: Ht 200mm(8") Dia 100 mm(4")
Ref ltr no : PDCAS/78 of 2024-2025/218/E-6 Dt.16 Nov'2025. Type of Aggregate : Stone
Name of the project : Construction of 1 X 52 (B+G+13) Officer's Studio type Apartment. Brand &Type of Cement : Shah Opc.
Status of sample : 9th floor roof slab. Proportion of Mixture : 1:1.25:2.5
Dt of sample collection: 17 Nov'2025 Desired Design Strength : 4000 Psi
Test Standard : ASTM/BS

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	11 Nov'2025 (28 days)	09 Dec'2025	12.17	46214.03	3797	Average of Sample 2 & 3 2858	Combined Failure
2			12.17	35899.52	2950		
3			12.17	33666.03	2766		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

- 1 As the strength is below the desired design strength, so nec. measures to be taken as per particular specifications of contract.

Laboratory Technician

Test Performed By

Vetted By