



**MATERIAL TESTING LABORATORY  
MILITARY ENGINEER SERVICES(MES)**

Page No : 129

Copy no : 01

**TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE**

Job No : 129(D)/2025-2026 (Con).

Name of Client : AGE (Army) Momenshahi.

Sample Specimen: Ht 200mm(8") Dia 100 mm(4")

Ref ltr no : CEA/719 of 2021-2022/52/E-6 Dt.17 Nov'2025.

Type of Aggregate : Stone

Name of the project : Construction of new building.

Brand &Type of Cement : Shah Opc.

Status of sample : Roof slab (2nd floor).

Proportion of Mixture : 1:1.5:3

Dt of sample collection: 18 Nov'2025

Desired Design Strength : 2275 Psi

Test Standard : ASTM/BS

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	11 Nov'2025 (07 days)	18 Nov'2025	12.17	31946.24	2625	Average of Sample 1, 2 & 3 2430	Combined Failure
2			12.17	30673.16	2520		
3			12.17	26094.51	2144		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By