



**MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)**

Page No: 366

Copy no : 02

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 132(D)/2025-2026 (Con).
Name of Client : GE (Navy) Dhaka. Sample Specimen : Ht 200mm(8") Dia 100 mm(4")
Ref Itr no : 6000/Naval HQ CW & MC/100/E-6 Dt.16 Nov'2025. Type of Aggregate Stone
Name of the project : Construction of CW & MC and Multipurpose Complex. Brand &Type of Cement : Shah Opc.
Status of sample : 3rd floor roof. Proportion of Mixture : 1:1.5:3
Dt of sample collection: 18 Nov'2025 Desired Design Strength : 2100 Psi
Test Standard : ASTM/BS

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	12 Nov'2025 (07 days)	19 Nov'2025	12.17	26585.87	2185	Average of Sample 1 & 3 2177	Combined Failure
2			12.17	18212.53	1497		
3			12.17	26407.19	2170		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm²=14.223 Psi]