



**MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)**

Page No: 133

Copy no : 01

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 133(D)/2025-2026 (Con).
Name of Client : GE (Navy) Khulna. Sample Specimen : Ht 200mm(8") Dia 100 mm(4")
Ref Itr no : EinC/333 of 2022-2023/69/E-6 Dt.17 Nov'2025. Type of Aggregate : Stone
Name of the project : Construction of 1 x Bellmen Hanger. Brand &Type of Cement : Elephant Opc.
Status of sample : RCC Mezzanine floor roof. Proportion of Mixture : 1:2.894:2.698 (Admixture).
Dt of sample collection: 19 Nov'2025 Desired Design Strength : 2600 Psi
Test Standard : ASTM/BS

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	13 Nov'2025 (07 days)	20 Nov'2025	12.17	26712.42	2195	Average of Sample 2 & 3 1246	Combined Failure
2			12.17	14956.10	1229		
3			12.17	15371.53	1263		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

- 1 As the strength is below the desired design strength, so nec. measures to be taken as per particular specifications of contract.

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm²=14.223 Psi]