



**MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)**

Page No : 134

Copy no : 01

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 134(D)/2025-2026 (Con).

Name of Client : GE (Air) Tejgaon, Dhaka.

Sample Specimen : Ht 200mm(8") Dia 100 mm(4")

Ref Itr no : CE Air/239 of 2024-2025/40/E-6 Dt.19 Nov'2025.

Type of Aggregate : Stone

Name of the project : Construction of Medical Squadron (MI Room).

Brand &Type of Cement : Crown Opc.

Status of sample : 3rd floor roof beam & Slab.

Proportion of Mixture : 1:1.5:3

Dt of sample collection: 20 Nov'2025

Desired Design Strength : 2600 Psi

Test Standard : ASTM/BS

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	14 Nov'2025 (07 days)	21 Nov'2025	12.17	36463.22	2996	Average of Sample 1, 2 & 3 2850	Combined Failure
2			12.17	31929.56	2624		
3			12.17	35665.85	2931		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm²=14.223 Psi]