

MATERIAL TESTING LABORATORYPage No : 194MILITARY ENGINEER SERVICES(MES)Copy no : 01

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 139/2024-2025 (Con).

Name of Client : GE (Navy) Khulna. Sample Specimen: Ht 200mm(8") Dia 100 mm(4")

Ref ltr no : 6000/Test/35 /E-6 Dt.07 Sep'2025. Type of Aggregate : Stone

Name of the project : Construction of 05 Story Barrack (Last Phase of 4th Phase). Brand &Type of Cement : Seven ring Opc.

Status of sample : 4th floor Column. Proportion of Mixture : 1:1.5:3

Dt of sample collection: 08 Sep'2025 Desired Design Strength : 1950 Psi

Test Standard: ASTM/BS

Ser no.	Date of casting	Date of Test	Specimen	Maximum Load	Crushing	Average	Remarks
	and		Area	(Lbs)	Strength	Crushing	
	(Age in days)		Sq inch		(Psi)	Strength	
						(Psi)	
1	02 Sep'2025 (07 days)	09 Sep'2025	12.17	30220.89	2483	Average of Sample 1, 2 & 3	Combined Failure
2			12.17	29127.34	2393		
3			12.17	26211.21	2154		

Cautions:

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- In oder to be avoid fraudulent fabrication of the test result, it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician	Test Performed By	<u>Vetted By</u>
-----------------------	-------------------	------------------