



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)

Page No : 373

Copy no : 01

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 141(D)/2025-2026 (Con).

Name of Client : GE (Navy) Khulna.

Sample Specimen: Ht 200mm(8") Dia 100 mm(4")

Ref ltr no : CEN/226 of 2024-2025/07/E-6 Dt.23 Nov'2025.

Type of Aggregate : Stone

Name of the project : Construction of 1 x 56 'B" Type & 'C' Type Officer's Qtr.

Brand &Type of Cement : Crown Opc.

Status of sample : Ground floor roof.

Proportion of Mixture : 1:1.5:3

Dt of sample collection: 24 Nov'2025

Desired Design Strength : 2600 Psi

Test Standard : ASTM/BS

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	17 Nov'2025 (07 days)	24 Nov'2025	12.17	39470.48	3243	Average of Sample 1, 2 & 3 3072	Combined Failure
2			12.17	38490.84	3163		
3			12.17	34185.00	2809		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By