



**MATERIAL TESTING LABORATORY  
MILITARY ENGINEER SERVICES(MES)**

Page No : 447

Copy no : 02

**TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE**

Job No : 155(D)/2025-2026 (Con).

Name of Client : GE (Navy) Khulna.

Sample Specimen: Ht 200mm(8") Dia 100 mm(4")

Ref ltr no : EinC/13 of 2025-2026/13/E-6 Dt.27 Nov'2025.

Type of Aggregate : Stone

Name of the project : Construction of 1 x Multipurpose Building.

Brand &Type of Cement : Bashundhara Opc.

Status of sample : 3rd floor column.

Proportion of Mixture : 1:2.648:2.505 (Admixture).

Dt of sample collection: 30 Nov'2025

Desired Design Strength : 4500 Psi

Test Standard : ASTM/BS

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	23 Nov'2025 (28 days)	21 Dec'2025	12.17	53879.09	4427	Average of Sample 1 & 3 4614	Combined Failure
2			12.17	49322.77	4053		
3			12.17	58435.40	4802		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By