



MATERIALS TESTING LABORATORY MILITARY ENGINEER SERVICES(MES)

Page no: 68

TEST RESULT FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S BARS

Job No : 16/2025-2026 (Steel).

Copy No : 05

Name of Client : GE (Army) Sylhet.

Sample Specimen : Length 600mm , Dia 25mm

Ref.ltr.No : CEA/312 of 2024-2025/05/E-6 Dt.14 July'2025.

Sample Grade : 60

Project Name : Construction of 1 x 760 Men SMBK Complex-9.

Frog Mark : RSM B-420 DWR.

Dt. of Sample Collection: 17 July'2025

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof load	Yield or Proof Strength	Average Yield or Proof load	Ultimate load	Ultimate Strength	Average Ultimate Strength	Ratio	Elongation% (gauge length)		Average Elongation% (gauge length)	
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	(Fult/Fy)	8inch	5d	8inch	5d
1	0.984 25.00	0.991 25.16	0.7609 490.8739	2.624 3.904	2.624 3.904	60320.63 268.32	79280 547	79271 547	79935.06 355.57	105059 725	105725 729	1.33	24		25	
2	0.984 25.00	0.991 25.16	0.7609 490.8739	2.624 3.904		60001.40 266.90	78860 544		79477.03 353.53	104457 720		1.32	23.5			
3	0.984 25.00	0.991 25.16	0.7609 490.8739	2.624 3.904		60619.05 269.65	79672 549		81912.93 364.37	107659 742		1.35	26.5			

Cautions:

1. Samples as supplied to the laboratory have been tested.The laboratory authority does not bear any responsibility as to the representative charecture of the samples to be tested.
2. It is recommended that samples are Sent in asecuried and sealed cover/packet/container under signature of the competent authority.
3. In order to avoid fraudulent of the test results,it is recommended that all test reports should be collected by duly authorised person and not by contractor/supplier.

Ovservation on Specimen(if any):

Minimum Standard Requirements (BDS/ISO 6935-2:1991(E))				Minimum Standard Requirments(ASTM A615/A616M-96a)									
				ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M			
Grade	Y/strength N/mm2 or Mpa	Ult.Str N/mm2 or Mpa	Elongation %	Grade	Y/strength psi (kg/cm2)	Ult.Str psi (kg/cm2)	Grade	Y/strength Mpa (kg/cm2)	Ult.Str Mpa (kg/cm2)	Minimum Elongation in 8"(203.2 mm) GL (%)			
										10 mm	13,16,19 mm	22,25 mm	29,32,36 mm
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12	..	..
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)	..	7	7	6

Laboratory Technician

Test Performed By

Vetted By