



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)

Page No: 466

Copy no : 02

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 168(D)/2025-2026 (Con).
Name of Client : GE (Army) Ghatal.
Ref ltr no : CEA /439 of 2021-2022/95/E-6 Dt.02 Dec'2025.
Name of the project : Construction of underground fuel tanks,fuel dispensing unit etc.
Status of sample : Boundary wall RCC foundation and column casting.
Dt of sample collection: 03 Dec'2025
Test Standard : ASTM/BS

Sample Specimen : Ht 200mm(8") Dia 100 mm(4")
Type of Aggregate : Brick
Brand &Type of Cement : Elephant Opc.
Proportion of Mixture : 1:1.5:3
Desired Design Strength : 3000 Psi

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	27 Nov'2025 (28 days)	25 Dec'2025	12.17	41174.18	3383	Average of Sample 1, 2 & 3 3372	Combined Failure
2			12.17	40309.65	3312		
3			12.17	41629.19	3421		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to be avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm²=14.223 Psi]