



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)

Page No: 409

Copy no : 01

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 172(D)/2025-2026 (Con).

Name of Client : GE (Army) Sylhet.

Ref ltr no : CEA/76 of 2025-2026/08/E-6 Dt.02 Dec'2025.

Name of the project : Construction of 300 Bedded Combined Military Hospital(CMH).

Status of sample : 4th floor Column & Roof Beam.

Dt of sample collection: 04 Dec'2025

Test Standard : ASTM/BS

Sample Specimen : Ht 200mm(8") Dia 100 mm(4")

Type of Aggregate : Stone

Brand &Type of Cement : Seven Rings Opc.

Proportion of Mixture : 1:1.25:2.50

Desired Design Strength : 2600 Psi

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	28 Nov'2025 (07 days)	05 Dec'2025	12.17	34961.45	2873	Average of Sample 1, 2 & 3 2733	Combined Failure
2			12.17	33062.99	2717		
3			12.17	31767.56	2610		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to be avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

- 1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm²=14.223 Psi]