



**MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)**

Page No: 419

Copy no : 01

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 177(D)/2025-2026 (Con).
Name of Client : AGE (Air) Shamshernagar. Sample Specimen : Ht 200mm(8") Dia 100 mm(4")
Ref Itr no : CE Air/177 of 2024-2025/08/E-6 Dt.07 Dec'2025. Type of Aggregate : Stone
Name of the project : Construction of Airmen type Qtr. Brand &Type of Cement : Seven rings Opc.
Status of sample : 2nd floor roof slab. Proportion of Mixture : 1:1.5:3
Dt of sample collection: 07 Dec'2025 Desired Design Strength : 2356 Psi
Test Standard : ASTM/BS

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	03 Dec'2025 (07 days)	10 Dec'2025	12.17	18319.74	1505	Average of Sample 2 & 3 2412	Combined Failure
2			12.17	31291.65	2571		
3			12.17	27418.67	2253		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm²=14.223 Psi]