



**MATERIAL TESTING LABORATORY  
MILITARY ENGINEER SERVICES(MES)**

Page No: 487

Copy no : 02

**TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE**

Job No : 186(D)/2025-2026 (Con).  
Name of Client : GE (Army) Cumilla.  
Ref Itr no : CEA/256 of 2022-2023/64/E-6 Dt.08 Dec'2025.  
Name of the project : Construction of 1 X 56 family Qtr.  
Status of sample : Ground floor column.  
Dt of sample collection: 09 Dec'2025  
Test Standard : ASTM/BS

Sample Specimen : Ht 200mm(8") Dia 100 mm(4")  
Type of Aggregate : Stone  
Brand & Type of Cement : Royal Opc.  
Proportion of Mixture : 1:1.25:2.5  
Desired Design Strength : 4500 Psi

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	03 Dec'2025 (28 days)	31 Dec'2025	12.17	56576.45	4649	Average of Sample 1 & 2 4625	Combined Failure
2			12.17	56007.68	4602		
3			12.17	54255.87	4458		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result, it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

**Observation on Specimen(if any):**

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm<sup>2</sup>=14.223 Psi]