



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)

Page No: 328

Copy no : 02

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 199/2025-2026 (Con).
Name of Client : GE (Army) Central,Dhaka
Ref ltr no : EinC/18 of 2024-2025/132/E-6 Dt.15 Oct'2025.
Name of the project : Construction of Boundary wall.
Status of sample : Foundation & Column.
Dt of sample collection : 15 Oct'2025
Test Standard : ASTM/BS

Sample Specimen : Ht 200mm(8") Dia 100 mm(4")
Type of Aggregate : Brick
Brand &Type of Cement : Shah Opc.
Proportion of Mixture : 1:2:4
Desired Design Strength : 2500 Psi

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	13 Oct'2025 (28 days)	10 Nov'2025	12.17	32362.42	2659	Average of Sample 1, 2 & 3 2731	Combined Failure
2			12.17	34549.52	2839		
3			12.17	32795.28	2695		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result, it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm²=14.223 Psi]