



**MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)**

Page No: 492

Copy no : 02

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 199(D)/2025-2026 (Con).

Name of Client : GE (Air) Tejgaon, Dhaka.

Sample Specimen : Ht 200mm(8") Dia 100 mm(4")

Ref Itr no : CE Air/197 of 2024-2025/41/E-6 Dt.14 Dec'2025.

Type of Aggregate : Stone

Name of the project : Construction of Base HQ.

Brand &Type of Cement : Crown Opc.

Status of sample : Ground floor beam.

Proportion of Mixture : 1:1.5:3

Dt of sample collection: 15 Dec'2025

Desired Design Strength : 4000 Psi

Test Standard : ASTM/BS

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	08 Dec'2025 (28 days)	05 Jan'2026	12.17	57691.24	4740	Average of Sample 1, 2 & 3 4510	Combined Failure
2			12.17	54551.63	4482		
3			12.17	52413.06	4307		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm²=14.223 Psi]