



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)

Page No: 311

Copy no : 01

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 209/2025-2026 (Con).
Name of Client : GE (Air) Tejgaon,Dhaka.
Ref ltr no : CE Air/185 of 2024-2025/11/E-6 Dt.26 Oct'2025.
Name of the project : Construction of 1 x 72 Airmen type Qtr.
Status of sample : 10th floor roof beam & Slab.
Dt of sample collection: 28 Oct'2025
Test Standard : ASTM/BS

Sample Specimen : Ht 200mm(8") Dia 100 mm(4")
Type of Aggregate : Stone
Brand &Type of Cement : Shah Opc.
Proportion of Mixture : 1:1.5:3
Desired Design Strength : 2600 Psi

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	22 Oct'2025 (07 days)	29 Oct'2025	12.17	35609.16	2926	Average of Sample 1, 2 & 3 2782	Combined Failure
2			12.17	32973.65	2709		
3			12.17	32973.65	2709		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result, it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm2=14.223 Psi]