



**MATERIAL TESTING LABORATORY  
MILITARY ENGINEER SERVICES(MES)**

Page No: 483

Copy no : 01

**TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE**

Job No : 210(D)/2025-2026 (Con).

Name of Client : GE (Army) Cumilla.

Sample Specimen : Ht 200mm(8") Dia 100 mm(4")

Ref Itr no : CEA/39 of 2025-2026/06/E-6 Dt.28 Dec'2025.

Type of Aggregate : Stone

Name of the project : Construction of 1 x SMBK and CH/DH & Recreation Room.

Brand &Type of Cement : Crown Opc.

Status of sample : Ground floor roof.

Proportion of Mixture : 1:1.5:3

Dt of sample collection: 29 Dec'2025

Desired Design Strength : 2275 Psi

Test Standard : ASTM/BS

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	22 Dec'2025 (07 days)	29 Dec'2025	12.17	45542.32	3742	***	Combined Failure
2			12.17	13798.17	1134		
3			12.17	27614.72	2269		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result, it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

**Observation on Specimen(if any):**

- 1 As per BNBC-2020 para No. 5.12.3.3 difference between provided samples are greater than 500 Psi. So no average result will be generated from this sample.

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm<sup>2</sup>=14.223 Psi]