



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)

Page No : 374
Copy no : 02

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 215/2025-2026 (Con).
Name of Client : GE (Air) Tejgaon, Dhaka. Sample Specimen: Ht 200mm(8") Dia 100 mm(4")
Ref ltr no : CE Air/185 of 2024-2025/13/E-6 Dt.28 Oct'2025. Type of Aggregate : Stone
Name of the project : Construction of 1x 72 Airmen Type Qtr. Brand &Type of Cement : Seven rings Opc.
Status of sample : 11th floor Column, Lift, Stair & shear wall. Proportion of Mixture : 1:1.25:2.50
Dt of sample collection: 03 Nov'2025 Desired Design Strength : 4500 Psi
Test Standard : ASTM/BS

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	28 Oct' 2025 (28 days)	25 Nov'2025	12.17	64508.17	5301	Average of Sample 1, 2 & 3 5025	Combined Failure
2			12.17	58516.44	4808		
3			12.17	60430.15	4966		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By