



**MATERIAL TESTING LABORATORY**  
**MILITARY ENGINEER SERVICES(MES)**

Page No : 319

Copy no : 01

**TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE**

Job No : 215/2025-2026 (Con).  
Name of Client : GE (Air) Tejgaon,Dhaka.  
Ref ltr no : CE Air/185 of 2024-2025/13/E-6 Dt.28 Oct'2025.  
Name of the project : Construction of 1x 72 Airmen Type Qtr.  
Status of sample : 11th floor Column, Lift, Stair & shear wall.  
Dt of sample collection: 03 Nov'2025  
Test Standard : ASTM/BS

Sample Specimen: Ht 200mm(8") Dia 100 mm(4")  
Type of Aggregate : Stone  
Brand &Type of Cement : Seven rings Opc.  
Proportion of Mixture : 1:1.25:2.50  
Desired Design Strength : 2800 Psi

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	28 Oct' 2025 (07 days)	04 Nov'2025	12.17	42158.79	3464	Average of Sample 1, 2 & 3  3296	Combined Failure
2			12.17	39903.34	3279		
3			12.17	38263.02	3144		

**Cautions :**

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to be avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

**Observation on Specimen(if any):**

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm<sup>2</sup>=14.223 Psi]