



**MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)**

Page No: 398

Copy no : 02

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 220/2025-2026 (Con).
Name of Client : GE (Air) Tejgaon, Dhaka. Sample Specimen : Ht 200mm(8") Dia 100 mm(4")
Ref Itr no : CE Air/179 of 2024-2025/33/E-6 Dt.10 Nov'2025. Type of Aggregate : Stone
Name of the project : Construction of 1 x Basement & BOQ. Brand &Type of Cement : Shah Opc.
Status of sample : Retaining wall & Column. Proportion of Mixture : Not Mentioned.
Dt of sample collection: 12 Nov'2025 Desired Design Strength : 5510 Psi (38.00 Mpa).
Test Standard : ASTM/BS

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	05 Nov'2025 (28 days)	03 Dec'2025	12.17	67287.60	5529	Average of Sample 1 & 3 5419	Combined Failure
2			12.17	58681.09	4822		
3			12.17	64622.16	5310		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

- 1 As the strength is below the desired design strength, so nec. measures to be taken as per particular specifications of contract.

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm²=14.223 Psi]