



**MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)**

Page No : 410

Copy no : 01

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 226/2025-2026 (Con).

Name of Client : GE (Army) Savar.

Sample Specimen: Ht 200mm(8") Dia 100 mm(4")

Ref ltr no : CEA/391 of 2024-2025/18/E-6 Dt.03 Dec' 2025.

Type of Aggregate : Stone

Name of the project : Construction of 1 X SMBK Complex.

Brand &Type of Cement : Seven rings Opc.

Status of sample : 3rd floor Column,beam,stairs and posts,struts.

Proportion of Mixture : 1:1.5:3

Dt of sample collection: 04 Dec'2025

Desired Design Strength : Not mentioned.

Test Standard : ASTM/BS

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	01 Dec'2025 (07 days)	08 Dec'2025	12.17	34425.41	2829	Average of Sample 1, 2 & 3 2613	Combined Failure
2			12.17	29779.76	2447		
3			12.17	31209.19	2564		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By