



**MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)**

Page No : 478

Copy no : 02

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 226/2025-2026 (Con).
Name of Client : GE (Army) Savar.
Ref ltr no : CEA/391 of 2024-2025/18/E-6 Dt.03 Dec' 2025.
Name of the project : Construction of 1 X SMBK Complex.
Status of sample : 3rd floor Column,beam,stairs and posts,struts.
Dt of sample collection: 04 Dec'2025
Test Standard : ASTM/BS

Sample Specimen: Ht 200mm(8") Dia 100 mm(4")
Type of Aggregate : Stone
Brand &Type of Cement : Seven rings Opc.
Proportion of Mixture : 1:1.5:3
Desired Design Strength : Not mentioned.

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	01 Dec'2025 (28 days)	29 Dec'2025	12.17	60489.58	4970	Average of Sample 1 & 3 5052	Combined Failure
2			12.17	55802.92	4585		
3			12.17	62468.90	5133		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By