



**MATERIAL TESTING LABORATORY  
MILITARY ENGINEER SERVICES(MES)**

Page No: 475

Copy no : 02

**TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE**

Job No : 228/2025-2026 (Con).  
Name of Client : GE (Air) Tejgaon, Dhaka. Sample Specimen : Ht 200mm(8") Dia 100 mm(4")  
Ref Itr no : CE Air/185 of 2024-2025/22/E-6 Dt.02 Dec'2025. Type of Aggregate : Stone  
Name of the project : Construction of 1 x 72 Airmen type Qtr. Brand &Type of Cement : Shah Opc.  
Status of sample : 13th floor column, Lift, Stair & Shear wall. Proportion of Mixture : 1:1.25:2.5  
Dt of sample collection: 07 Dec'2025 Desired Design Strength : 4500 Psi  
Test Standard : ASTM/BS

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	30 Nov'2025 (28 days)	28 Dec'2025	12.17	58942.53	4843	Average of Sample 1, 2 & 3  4682	Combined Failure
2			12.17	56121.43	4611		
3			12.17	55893.93	4593		

**Cautions :**

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

**Observation on Specimen(if any):**

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm<sup>2</sup>=14.223 Psi]