



**MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)**

Page No: 493

Copy no : 02

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 236/2025-2026 (Con).
Name of Client : GE (Air) Tejgaon, Dhaka. Sample Specimen : Ht 200mm(8") Dia 100 mm(4")
Ref Itr no : CE Air/24 of 2025-2026/28/E-6 Dt.14 Dec'2025. Type of Aggregate : Stone
Name of the project : Construction of 1 x Hangar. Brand &Type of Cement : Shah Opc.
Status of sample : Ground floor roof. Proportion of Mixture : 1:1.5:3
Dt of sample collection: 15 Dec'2025 Desired Design Strength : 3500 Psi
Test Standard : ASTM/BS

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	08 Dec'2025 (28 days)	05 Jan'2026	12.17	50365.49	4138	Average of Sample 1 & 2 4218	Combined Failure
2			12.17	52299.30	4297		
3			12.17	60034.57	4933		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm²=14.223 Psi]