



**MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)**

Page No: 444

Copy no : 01

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 238/2025-2026 (Con).
Name of Client : GE (Army) Barishal. Sample Specimen : Ht 200mm(8") Dia 100 mm(4")
Ref Itr no : CEA/02 of 2025-2026/13/E-6 Dt.15 Dec'2025. Type of Aggregate : Brick
Name of the project : Construction of fresh Food storage Chiller room and cold storage. Brand &Type of Cement : Seven rings Opc.
Status of sample : RCC Road. Proportion of Mixture : 1:2:4
Dt of sample collection: 17 Dec'2025 Desired Design Strength : 1650 Psi
Test Standard : ASTM/BS

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	10 Dec'2025 (07 days)	17 Dec'2025	12.17	22587.93	1856	Average of Sample 1, 2 & 3 1964	Combined Failure
2			12.17	24933.09	2049		
3			12.17	24196.04	1988		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm²=14.223 Psi]