



**MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)**

Page No: 504

Copy no : 02

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 239/2025-2026 (Con).

Name of Client : AGE (Army) Rajendrapur.

Sample Specimen : Ht 200mm(8") Dia 100 mm(4")

Ref Itr no : CEA/354 of 2022-2023/55/E-6 Dt.17 Dec'2025.

Type of Aggregate : Stone

Name of the project : Construction of 1 x 52 C/D Type Officer's Qtr.

Brand &Type of Cement : Shah Opc.

Status of sample : Wall, Column, Posts & Struts (4th floor).

Proportion of Mixture : 1:1.25:2.5

Dt of sample collection: 18 Dec'2025

Desired Design Strength : 4500 Psi

Test Standard : ASTM/BS

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	12 Dec'2025 (28 days)	09 Jan'2026	12.17	58624.02	4817	Average of Sample 1, 2 & 3 4749	Combined Failure
2			12.17	57736.74	4744		
3			12.17	57008.71	4684		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm²=14.223 Psi]