



**MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)**

Page No : 410

Copy no : 02

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 244/2025-2026 (Con).

Name of Client : GE (Navy) Khulna.

Sample Specimen: Ht 200mm(8") Dia 100 mm(4")

Ref ltr no : CEN/91 of 2024-2025/24/E-6 Dt.21 Dec'2025.

Type of Aggregate : Stone

Name of the project : Construction of MT Pool.

Brand &Type of Cement : Shah Opc.

Status of sample : Floor Casting.

Proportion of Mixture : 1:1.5:3

Dt of sample collection: 22 Dec'2025

Desired Design Strength : 4000 Psi

Test Standard : ASTM/BS

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	15 Dec'2025 (28 days)	12 Jan'2026	12.17	59330.39	4875	Average of Sample 2 & 3 5614	Combined Failure
2			12.17	70745.75	5813		
3			12.17	65889.92	5414		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By