



**MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)**

Page No: 528

Copy no : 02

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 246/2025-2026 (Con).

Name of Client : GE (Army) Barishal.

Sample Specimen : Ht 200mm(8") Dia 100 mm(4")

Ref Itr no : CEA/123 of 2025-2026/07/E-6 Dt.24 Dec'2025.

Type of Aggregate : Brick

Name of the project : Construction of Barbed Wire Fencing with RCC Post.

Brand &Type of Cement : Seven rings Opc.

Status of sample : Barbed Wire Fencing Pillar.

Proportion of Mixture : 1:2:4

Dt of sample collection: 28 Dec'2025

Desired Design Strength : 2500 Psi

Test Standard : ASTM/BS

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	21 Dec'2025 (28 days)	18 Jan'2026	12.17	37693.31	3097	Average of Sample 1, 2 & 3 3022	Combined Failure
2			12.17	37261.04	3062		
3			12.17	35395.48	2908		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm²=14.223 Psi]