



**MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)**

Page No: 481

Copy no : 01

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 248/2025-2026 (Con).
Name of Client : GE (Air) Tejgaon, Dhaka. Sample Specimen : Ht 200mm(8") Dia 100 mm(4")
Ref Itr no : CE Air/245 of 2024-2025/20/E-6 Dt.23 Dec'2025. Type of Aggregate : Stone
Name of the project : Construction of 31 sqn. Brand &Type of Cement : Crown Opc.
Status of sample : 3rd floor roof. Proportion of Mixture : 1:1.5:3
Dt of sample collection: 29 Dec'2025 Desired Design Strength : 2600 Psi
Test Standard : ASTM/BS

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	22 Dec'2025 (07 days)	29 Dec'2025	12.17	84355.14	6931	Average of Sample 2 & 3 7861	Combined Failure
2			12.17	97755.35	8032		
3			12.17	93591.95	7690		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

- 1 The strength of this concrete is higher than the normal concrete.

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm²=14.223 Psi]