



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES (MES)
TEST RESULT FOR FINENESS MODULUS(F.M.) OF SAND.

Page No: 41

Copy no : 01

Job No : 25/2025-2026 (Sand).
Name of Clint : GE (Navy) Patuakhali.
Ref ltr no : EinC/73 of 2024-2025/40/E-6 Dt.10 Aug'2025
Project Name : Provision of Firefighting system.
Sample Specimen : Sylhet Sand.
Dt of sample collection : 11 Aug'2025
Test Standard : ASTM/BS

Sieve Size	Wt of Material Retained(gms)	Percentage Material Retained(Round)	Cumulative % Retained	%Finer	Remarks
# 4	1.99	0.50	0.50		
# 8	7.54	1.89	2.38		
#16	52.03	13.01	15.39		
# 30	182.06	45.52	60.91		
# 50	146.05	36.51	97.42		FM= 2.77
#100	10.39	2.60	100.02		
# 200	0	0.00	..		
#Pan	0	0.00	...		
			Σ= 276.61		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to be avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Permissible Value:

- 1.For Sylhet/Domar sand minimum FM will be = 2.50
- 2.For Local sand minimum FM will be = 1.5
- 3.For Vitty sand minimum FM will be = 0.80