



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)

Page No: 484

Copy no : 01

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 250/2025-2026 (Con).

Name of Client : GE (Navy) Khulna.

Ref ltr no : 6000/Test/43/E-6 Dt.29 Dec'2025.

Name of the project : Construction of SMBK.

Status of sample : 4th floor roof.

Dt of sample collection: 30 Dec'2025

Test Standard : ASTM/BS

Sample Specimen : Ht 200mm(8") Dia 100 mm(4")

Type of Aggregate : Stone

Brand &Type of Cement : Seven rings Opc.

Proportion of Mixture : 1:1.5:3

Desired Design Strength : 1950 Psi

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	23 Dec'2025 (07 days)	30 Dec'2025	12.17	27364.46	2249	Average of Sample 1, 2 & 3 2297	Combined Failure
2			12.17	27364.46	2249		
3			12.17	29139.02	2394		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to be avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm2=14.223 Psi]