MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 254/2025-2026 (Con).
Name of Client : AGE (Air) Cox's Bazar.
Ref ltr no : CE (Air)/234 of 2024-2025/10/E-6 Dt.07 Jan'2026
Name of the project : Construction of Rcc Travers.
Status of sample : Travers wall.
Dt of sample collection: 08 Jan'2026
Test Standard : ASTM/BS

Sample Specimen: Ht 200mm(8") Dia 100 mm(4")
Type of Aggregate : Stone
Brand &Type of Cement : Daimond Opc.
Proportion of Mixture : 1:1.25:2.5
Desired Design Strength : 2600 Psi.

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	01 Jan'2026 (07 days)	08 Jan'2026	12.17	33097.65	2720	Average of Sample 1 , 2 & 3	Combined Failure
2			12.17	34872.21	2865		
3			12.17	32665.39	2684	2756	

Cautions :

1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.

2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority

3 In oder to be avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician Test Performed By Vetted By

Note:[1 Mpa=145 psi, 1kg/cm2=14.223 Psi]