



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES (MES)
TEST RESULT FOR FINENESS MODULUS(F.M.) OF SAND.

Page No: 34

Copy no : 01

Job No : 34/2025-2026 (Sand).
Name of Clint : GE (Army) Rangpur.
Ref ltr no : EinC/155 of 2024-2025/15/E-6 Dt.01 Sep'2025
Project Name : Construction of Road(RCC road/hardstanding).
Sample Specimen : Sylhet Sand.
Dt of sample collection : 02 Sep'2025
Test Standard : ASTM/BS

Sieve Size	Wt of Material Retained(gms)	Percentage Material Retained(Round)	Cumulative % Retained	%Finer	Remarks
# 4	3.52	0.88	0.88		
# 8	33.4	8.35	9.23		
#16	97.73	24.43	33.66		
# 30	128.48	32.12	65.78		
# 50	82.75	20.69	86.47		FM= 2.93
#100	40.56	10.14	96.61		
# 200	13.45	3.36	..		
#Pan	0	0.00	...		
			Σ= 292.64		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to be avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Permissible Value:

- 1.For Sylhet/Domar sand minimum FM will be = 2.50
- 2.For Local sand minimum FM will be = 1.5
- 3.For Vitty sand minimum FM will be = 0.80