



MILITARY ENGINEER SERVICES (MES)

M E S
Material Testing
Laboratory

MATERIAL TESTING LABORATORY

Mobile: 01769-012888, <http://mes.org.bd>

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 346/2025-2026 (Con). Type of Aggregate : Stone
Send by : GE (Army) Bogura. Brand & Type of Cement : Fresh Opc.
Ref. No : CEA/283 of 2022-2023/69/E-6 Dt.08 Apr'2026. Proportion of Mixture : 1:1.5:3
Project : Construction of 1 x 20 OR's Qtr. Desired Design Strength : 3500 Psi
Sample : Concrete Cylinder Date of Sample Collection : 09/04/2026
Location : 1st floor roof slab. Date of Test : 02/05/2026
Test : Compressive Strength Test of Concrete Cylinder [ASTM C39]

TEST REPORT

SL No.	Date of casting as per the letter	Specimen Designation/ Frog Mark	Specimen Area	Maximum Load	Crushing Strength	Average Crushing Strength	Mode of Failure
1	04 Apr'2026 (28 days)		(Sq. in)	(Lb)	(Psi)	(Psi)	
2		GE (Army)	12.17	53687.10	4411	4193 (28.91 Mpa)	Combined *
		GE (Army)	12.17	48909.44	4019		Combined *
3		GE (Army)	12.17	50479.24	4148	(294.80 kg/cm ²)	Combined *

Note: Samples were received in sealed condition.

*Combined = Mortar and Aggregate Failure.

Observation on Specimen(if any):


1





Report Prepared by :

Test Performed by :

Countersigned by :


MD. IKBAL HOSEN
SAE B/R
AHQ E in C 's Br
Wks Dte, Dhaka Cantt.


AHASAN HABIB
AE B/R
Actg SO-III (Lab)
AHQ E in C 's Br
Wks Dte, Dhaka Cantt.


MD ATIKUR RAHMAN
MAJOR
OIC (Lab)
AHQ E in C 's Br
Wks Dte, Dhaka Cantt.

[1 Mpa=145 psi, 1kg/cm²=14.223 Psi]

Important Note:

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to be avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

