




MILITARY ENGINEER SERVICES (MES)



MATERIAL TESTING LABORATORY

Mobile: 01769-012888, <http://mes.org.bd>

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 360/2025-2026 (Con). Type of Aggregate : Stone
Send by : GE (Navy) Khulna. Brand & Type of Cement : Crown Opc.
Ref. No : CEN/136 of 2025-2026 /11/E-6 Dt.27 Apr'2026. Proportion of Mixture : Mix Design.
Project : Construction of MT Pool. Desired Design Strength : 2925 Psi
Sample : Concrete Cylinder Date of Sample Collection : 29/04/2026
Location : 1st floor column. Date of Test : 29/04/2026
Test : Compressive Strength Test of Concrete Cylinder [ASTM C39]

TEST REPORT

SL No.	Date of casting as per the letter	Specimen Designation/ Frog Mark	Specimen Area (Sq. in)	Maximum Load (Lb)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Mode of Failure
1	22 Apr'2026 (7 days)						
2		GE (Navy)	12.17	42084.21	3458	3243 (22.36 Mpa)	Combined *
		GE (Navy)	12.17	38535.09	3166		Combined *
3	GE (Navy)	12.17	37784.31	3105	(228 kg/cm ²)	Combined *	

Note: Samples were received in sealed condition.

*Combined = Mortar and Aggregate Failure.

Observation on Specimen(if any):

1



Report Prepared by :

Test Performed by :

Countersigned by :

MD. IKBAL HOSSEN
SAE B/R
AHQ E in C's Br
Wks Dte, Dhaka Cantt.

AHASAN HABIB
AE B/R
Actg SO-III (Lab)
AHQ E in C's Br
Wks Dte, Dhaka Cantt.

MD ATIKUR RAHMAN
MAJOR
OIC (Lab)
AHQ E in C's Br
Wks Dte, Dhaka Cantt.

[1 Mpa=145 psi, 1kg/cm²=14.223 Psi]

Important Note:

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to be avoid fraudulent fabrication of the test result, it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

