

## MATERIAL TESTING LABORATORY MILITARY ENGINEER SERVICES(MES)

Page No: 544

Copy no: 01

## TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 395/2024-2025 (Con).

Name of Client : GE (Army) Jashore. Sample Specimen: Ht 200mm(8") Dia 100 mm(4")

Ref ltr no : EinC/137 of 2023-2024/73/E-6 Dt.01 Jan'2025. Type of Aggregate : Stone

Name of the project : Construction of 1 x OR's/Equivalent Qtr.

Brand &Type of Cement : Seven rings Opc.

Status of sample : 3rd floor Column, wall, beam, stair & landing etc. Proportion of Mixture : 1:1.5:3

Dt of sample collection: 02 Jan'2025

Desired Design Strength : 2356 Psi

Test Standard : ASTM/BS

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1			12.17	43070.08	3539	Average of Sample	

	, ,		•		` ,	(Psi)	
1			12.17	43070.08	3539	Average of Sample	
2	30 Dec '2024 (07 days)	06 Jan'2025	12.17	39789.43	3269	1, 2 & 3	Combined Failure
3			12.17	40632.38	3339	3382	

## Cautions:

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- In oder to be avoid fraudulent fabrication of the test result, it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

## Observation on Specimen(if any):

1

<u>Laboratory Technician</u> <u>Test Performed By</u> <u>Vetted By</u>

Note:[1 Mpa=145 psi, 1kg/cm2=14.223 Psi]