



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)

Page No : 547

Copy no : 01

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 413/2024-2025 (Con).
Name of Client : GE (Army) Mirpur.
Ref ltr no : CEA/378 of 2022-2023/43/E-6 Dt.31 Dec'2024.
Name of the project : Construction of 1 x Composite SMBK.
Status of sample : 4th floor Column.
Dt of sample collection: 06 Jan'2025
Test Standard : ASTM/BS

Sample Specimen: Ht 200mm(8") Dia 100 mm(4")
Type of Aggregate : Stone
Brand &Type of Cement : Scan Opc.
Proportion of Mixture : 1:1.25:2.5
Desired Design Strength : 2600 Psi

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	30 Dec '2024 (07 days)	06 Jan'2025	12.17	55418.05	4554	Average of Sample 1 & 2 4513	Combined Failure
2			12.17	54438.42	4473		
3			12.17	32726.94	2689		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to be avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm2=14.223 Psi]