



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)

Page No : 725

Copy no : 01

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 537/2024-2025 (Con).

Name of Client : GE (Navy) Khulna.

Ref ltr no : EinC/138 of 2023-2024/56/E-6 Dt.11 Mar'2025.

Name of the project : Construction of 1 x OR's/Equivalent residential building.

Status of sample : 1st floor roof.

Dt of sample collection: 12 Mar'2025

Test Standard : ASTM/BS

Sample Specimen: Ht 200mm(8") Dia 100 mm(4")

Type of Aggregate : Stone

Brand &Type of Cement : Seven rings Opc.

Proportion of Mixture : 1:1.5:3

Desired Design Strength : 2356 Psi.

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	05 Mar'2025 (07 days)	12 Mar'2025	12.17	36569.56	3005	Average of Sample 1, 2 & 3 2876	Combined Failure
2			12.17	34604.09	2843		
3			12.17	33822.37	2779		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result, it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm²=14.223 Psi]