



MATERIALS TESTING LABORATORY MILITARY ENGINEER SERVICES(MES)

Page no: 130

TEST RESULT FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S BARS

Job No : 56/2024-2025 (Steel).

Copy No : 01

Name of Client : AGE (Air) Cox's Bazar.

Sample Specimen : Length 600mm , Dia 10mm

Ref.ltr.No : EinC/190 of 2023-2024/07/E-6 Dt.13 Feb'2025.

Sample Grade : 60

Project Name : Construction of Road for 1 x Academic & Administrative Bldg.

Frog Mark : KSRM B-500 CWR.

Dt. of Sample Collection : 16 Feb'2025

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof load	Yield or Proof Strength	Average Yield or Proof load	Ultimate load	Ultimate Strength	Average Ultimate Strength	Ratio	Elongation% (gauge length)		Average Elongation% (gauge length)	
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	(Fult/Fy)	8inch	5d	8inch	5d
1	0.394 10.00	0.388 9.85	0.1217 78.5398	0.402 0.598	0.402 0.598	15298.55 68.05	125669 867	124452 858	17016.49 75.69	139781 964	139279 961	1.11	13.5		15	
2	0.394 10.00	0.388 9.85	0.1217 78.5398	0.402 0.598		15021.39 66.82	123392 851		16915.71 75.24	138953 958		1.13	17.5			
3	0.394 10.00	0.388 9.85	0.1217 78.5398	0.402 0.598		15131.34 67.31	124295 857		16934.03 75.33	139103 959		1.12	13			

Cautions:

1. Samples as supplied to the laboratory have been tested.The laboratory authority does not bear any responsibility as to the representative charecture of the samples to be tested.
2. It is recommended that samples are Sent in asecuried and sealed cover/packet/container under signature of the competent authority.
3. In order to avoid fraudulent of the test results,it is recommended that all test reports should be collected by duly authorised person and not by contractor/supplier.

Obsvration on Specimen(if any):

1. Diameter & Unit weight of 10 mm bar is less than the standard value but within tolerance limit according to MES Schedule of Rates-2016.

Minimum Standard Requirements (BDS/ISO 6935-2:1991(E))				Minimum Standard Requirments(ASTM A615/A616M-96a)									
				ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M			
Grade	Y/strength N/mm2 or Mpa	Ult.Str N/mm2 or Mpa	Elongation %	Grade	Y/strength psi (kg/cm2)	Ult.Str psi (kg/cm2)	Grade	Y/strength Mpa (kg/cm2)	Ult.Str Mpa (kg/cm2)	Minimum Elongation in 8"(203.2 mm) GL (%)			
										10 mm	13,16,19 mm	22,25 mm	29,32,36 mm
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12	..	..
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)	..	7	7	6

Laboratory Technician

Test Performed By

Vetted By

