

MATERIAL TESTING LABORATORY MILITARY ENGINEER SERVICES(MES)

Page No: 142

Copy no: 02

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 58/2025-2026 (Con).

Name of Client : GE (Army) Jalalabad. Sample Specimen: Ht 200mm(8") Dia 100 mm(4")

Ref ltr no : CEA/748 of 2021-2022/90/E-6 Dt.06 Aug'2025. Type of Aggregate : Stone

Name of the project : Construction of DS office complex. Brand &Type of Cement : Seven rings Opc.

Status of sample : Ground floor column. Proportion of Mixture : 1:1.25:2.5

Dt of sample collection: 07 Aug'2025 Desired Design Strength : 4000 Psi

Test Standard: ASTM/BS

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength	Remarks
1			12.17	66171.27	5437	(Psi)	
	24 11		12.17	00171.27	3437	Average of	
2	31 July'2025 (28 days)	28 Aug'2025	12.17	53322.09	4381	Sample 2 & 3	Combined Failure
3			12.17	52593.05	4322	4351	

Cautions:

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- In oder to be avoid fraudulent fabrication of the test result, it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

<u>Laboratory Technician</u> <u>Test Performed By</u>	<u>Vetted By</u>
---	------------------