

MATERIAL TESTING LABORATORYPage No : 92MILITARY ENGINEER SERVICES (MES)Copy no : 01

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 60/2025-2026 (Con).

Name of Client : GE (Army) Sylhet. Sample Specimen: Ht 200mm(8") Dia 100 mm(4")

Ref ltr no: CEA/341 of 2024-2025/08 /E-6 Dt. 04 Aug'2025.Type of Aggregate: StoneName of the project: Construction of 1 x 104 OR's Familly Qtr.Brand &Type of Cement : Shah Opc.Status of sample: 4th floor Column & Shear wall.Proportion of Mixture: 1:1.25:2.5Dt of sample collection: 07 Aug'2025Desired Design Strength : 2356 Psi

Test Standard : ASTM/BS

Ser no.	Date of casting	Date of Test	Specimen	Maximum Load	Crushing	Average	Remarks
	and		Area	(Lbs)	Strength	Crushing	
	(Age in days)		Sq inch		(Psi)	Strength	
						(Psi)	
1			12.17	30114.78	2475	Average of	
2	01 Aug'2025 (07 days)	08 Aug'2025	12.17	29712.76	2441	Sample 1, 2 & 3	Combined Failure
3			12.17	27702.62	2276	2397	

Cautions:

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- In oder to be avoid fraudulent fabrication of the test result, it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

<u>Laboratory Technician</u>	Test Performed By	Vetted By
------------------------------	-------------------	-----------