



**MATERIAL TESTING LABORATORY**  
**MILITARY ENGINEER SERVICE(MES)**

Page No : 830

Copy no : 01

**TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE**

Job No : 606/2024-2025 (Con).  
Name of Client : GE (Army) Central,Dhaka.  
Ref ltr no : EinC/91 of 2022-2023/133/E-6 Dt.04 May' 2025.  
Name of the project : Construction of 26 x JCO's Qtr and 52 x OR's Qtr.  
Status of sample : 12th floor column.  
Dt of sample collection: 04 May'2025  
Test Standard : ASTM/BS

Sample Specimen: Ht 200mm(8") Dia 100 mm(4")  
Type of Aggregate : Stone  
Brand &Type of Cement : Shah Opc.  
Proportion of Mixture : Not Mentioned.  
Desired Design Strength : 2925 Psi

| Ser no. | Date of casting and<br>(Age in days) | Date of Test | Specimen<br>Area<br>Sq inch | Maximum Load<br>(Lbs) | Crushing<br>Strength<br>(Psi) | Average<br>Crushing<br>Strength<br>(Psi)  | Remarks          |
|---------|--------------------------------------|--------------|-----------------------------|-----------------------|-------------------------------|---|------------------|
| 1       | 27 Apr'2025<br>(07 days)             | 04 May'2025  | 12.17                       | 43560.38              | 3579                          | Average of<br>Sample 1, 2 & 3<br><br>3658 | Combined Failure |
| 2       |                                      |              | 12.17                       | 45481.18              | 3737                          |   |                  |
| 3       |                                      |              | 12.17                       | 44520.78              | 3658                          |   |                  |

**Cautions :**

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

**Observation on Specimen(if any):**

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm<sup>2</sup>=14.223 Psi]