



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)

Page No : 862

Copy no : 01

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 621/2024-2025 (Con).
Name of Client : GE (Army) North, Dhaka.
Ref ltr no : CEA/316 of 2024-2025/02/ E-6 Dt.12 May' 2025.
Name of the project : Construction of 1 x Composite SM BK Complex.
Status of sample : 3rd floor Slab.
Dt of sample collection: 13 May'2025
Test Standard : ASTM/BS

Sample Specimen: Ht 200mm(8") Dia 100 mm(4")
Type of Aggregate : Stone
Brand &Type of Cement : Shah Opc.
Proportion of Mixture : 1:1.5:3
Desired Design Strength : 3150 Psi

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	01 May '2025 (14 days)	15 May'2025	12.17	46888.27	3853	Average of Sample 1, 2 & 3 3995	Combined Failure
2			12.17	49278.10	4049		
3			12.17	49680.13	4082		

Cautions :

- 1 Samples as supplied to the lab
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm²=14.223 Psi]